

C27450 Lead Free Brass No Silicon, No Bismuth, No Segregation (Comply with AB1953)

Chemical Composition % by weight

No.	Major chemical elements			
	Copper	Lead	Fe	Other
1	60-65	<0.25	<0.35	<0.5%

Room Temp Tensile & Hardness Data

No	Temper	Elongation	Tensile (KSI)	Yield (KSI)	Hardness
1	H02	30%	80	57	55-75

Fabrication Properites

Soldering	Excellent	Plating	Excellent
Brazing	Excellent	Forgability	95
Cold Working	Excellent	Machinability	70

Typical Uses



All CHENYEE Products are covered under 1 year limited warranty

2014 Chenyee Industries Co.,Ltd. - www.chenyeeindustries.com